(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau





(43) International Publication Date 27 May 2004 (27.05.2004)

(10) International Publication Number WO 2004/044251 A1

, ,	International Patent Classification7: C21D 8 International Application Number:	•	(71) Applicant (for all designated States except US): POSCO [KR/KR]; 1 Koedong-dong, Nam-ku, 790-300 Pohang, Kyungsangbook-do (KR).
(22)	PCT/KR2003/002 International Filing Date: 11 November 2003 (11.11.20)		 (72) Inventors; and (75) Inventors/Applicants (for US only): CHOI, Kyu-Seung [KR/KR]; c/o POSCO, 1 Koedong-dong, Nam-ku, 790-300 Pohang, Kyungsangbook-do (KR). WOO, Jong-Soo [KR/KR]; c/o POSCO, 1 Koedong-dong,
(25)	Filing Language: Kon	rean	Nam-ku, 790-300 Pohang, Kyungsangbook-do (KR).
(26)	Publication Language: Eng	glish	(74) Agent: C & S PATENT AND LAW OFFICE; C-2306 Daelim Acrotel, 467-6 Dogok-dong, Kangnam-gu, Seoul
(30)	Priority Data:		135-971 (KR).
	10-2002-0069646 11 November 2002 (11.11.2002) 10-2002-0069647	KR	(81) Designated States (national): CN, JP, US.
	11 November 2002 (11.11.2002) 10-2002-0074325	KR	(84) Designated States (regional): European patent (DE, FR, GB, IT).
	27 November 2002 (27.11.2002) 10-2002-0074326	KR	Published:
	27 November 2002 (27.11.2002) 10-2002-0074328	KR	with international search report
	27 November 2002 (27.11.2002) 10-2002-0074329	KR	For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the begin-
	27 November 2002 (27.11.2002)	KR	ning of each regular issue of the PCT Gazette.

(54) Title: COATING COMPOSITION, AND METHOD FOR MANUFACTURING HIGH SILICON ELECTRICAL STEEL SHEET USING THEREOF

(57) Abstract: There are provided a coating composition for siliconizing, and a method for manufacturing a high silicon electrical steel sheet using the same. The coating composition includes: a Fe-Si-based composite compound sintered powder having a grain size of - 325 mesh and containing 20 - 70 % silicon by weight; and a colloidal silica solution containing 15 - 30 part by weight of silica solid matter with respect to 100 part by weight of the sintered powder.